

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 362 874 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
19.11.2003 Bulletin 2003/47

(51) Int Cl.7: **C08G 18/62, C09D 175/04,
B05D 1/00**

(21) Application number: **03076734.7**

(22) Date of filing: **12.05.2003**

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PT RO SE SI SK TR**
Designated Extension States:
AL LT LV MK

(30) Priority: **15.05.2002 US 146162**

(71) Applicant: **E.I. DU PONT DE NEMOURS AND
COMPANY**
Wilmington Delaware 19898 (US)

(72) Inventors:
• **Millc, Richard**
Hradec Kralove, CZ-500 03 (CZ)
• **Kupcakova, Zdenka**
Pardubice, CZ-530 09 (CZ)

(74) Representative:
DuPont Performance Coatings Christine
Blering/Christine Kimpel
Dupont Performance Coatings GmbH & Co.KG,
Patent and License Departement,
Christbusch 25
42285 Wuppertal (DE)

(54) **A decorative coating composition for solid substrates**

(57) A coating composition comprising

- (a) 10 to 60 wt. % of one or more hydroxy-, carboxy- and/or amino-functionalized solid resins selected from the group of methacrylic resins, acrylic resins, polyester resins, polyurethane resins, epoxy modified resins with linear, branched or star structure,
- (b) 5 to 40 wt. % of one or more crosslinking agents for component (a),
- (c) 5 to 70 wt. % of a filler, such as, aluminum hydroxide,
- (d) 0 to 40 wt. % of a ground polymer material,
- (e) 0 to 35 wt. % of organic solvents,

- (f) 0.01 to 15 wt. % of additives and pigments and
- (g) 0 to 30 wt. % reactive thinners.

EP 1 362 874 A2

Description**Field of the Invention**

5 [0001] The invention relates to a coating composition for a substrate that provides a decorative surface having a stone, marble or granite-like effect and unique aesthetics and the resulting coated substrate can be used, for example, as building materials, for counter tops, wall panels, furniture, and for various other articles.

Background of the Invention

10 [0002] Coatings for substrates used in industrial and house-keeping fields, e.g., for surfaces in kitchens, baths and stores or for wall panels, furniture and other articles in home and business sectors, can have a solid color or stone, granite, or marble-like or other unique appearance.

15 [0003] Such coatings comprise a filled polymer composition that is cured at ambient temperature or can be forced-dried at elevated temperature. The coated articles can be costly to produce and difficult to transport and to install due to their heavy and brittle properties, e.g., they are fragile and easily chipped, broken or abused. The breakage rate at the required thickness makes these articles expensive.

20 [0004] Examples for known coatings and coated substrates are described as follows: JP 10128911, JP 8295548, JP 55126583, which relate to coating layers based on thermoplastic resins, such as, polyester, acrylic resins, and reinforced fiber.

[0005] US 5,789,032 relates to a curable composition including polyester resin and filler useful for the production of stone, marble, or granite effect coatings. A vibration action is needed to level the composition and to form an equable coating on the surface.

25 [0006] The present invention satisfies the demand for a decorative and robust coating for interior and exterior surfaces, especially for horizontal and vertical working tops, panels; furniture in homes, offices or industrial buildings; counter and dining tables, counter tops, floors; architectural facing of buildings and various articles (lamps, vases, picture frames, etc.) of all types. The coating composition is a highly filled composition comprising a selected solid resin, a filler, decorative granules or other aesthetic materials, and special additive systems.

Summary of the Invention

30 [0007] The present invention is directed to a high-filled coating composition comprising

35 (a) 10 to 60 wt % of one or more hydroxy-, carboxy- and/or amino-functionalized solid resins selected from the group of methacrylic resins, acrylic resins, polyester resins, polyurethane resins, epoxy modified resins with linear, branched or star structure,

(b) 5 to 40 wt. % of one or more crosslinking agents for component (a),

(c) 5 to 70 wt. % of a filler material,

(d) 0 to 40 wt. % of a ground polymer material,

40 (e) 0 to 35 wt. % of organic solvents,

(f) 0.01 to 15 wt. % of additives and pigments and

(g) 0 to 30 wt. % reactive thinners.

45 [0008] The composition can be formed as a flowable liquid or as a solid composition without organic solvent and reactive thinners and is cured after application on the substrate. The cured coating can be sanded and polished; and the final article can be cut into a desired shape if necessary.

[0009] Relating to the flowable liquid composition the component (b) comprises one or more polyisocyanates selected from the group consisting of blocked and unblocked polyisocyanates.

50 [0010] Relating to the solid composition without organic solvents and reactive thinners, the component (b) comprises one or more crosslinkers, such as hydroxyl, carboxyl, amide or amino groups containing crosslinkers, cycloaliphatic, aliphatic or aromatic polyisocyanates, epoxy groups containing crosslinkers or carboxy-functional polymers.

55 [0011] The appearance of the final coating prepared from the coating composition according to the invention is characterized by a solid and/or a stone-, granite-, marble-like appearance or other special aesthetic appearance. The articles produced with the coating composition according to the invention can be used as decorative surfaces, e.g., countertops, wall panels, for furniture, for floors, and for all types of various articles. The coatings and the coated products are robust and stable and are workable and repairable. The coatings can be applied in a factory or on location. They have an appearance of stone, cultured marble or granite, such as, the material Corian®. The coating composition can be applied on a vertical panel without sagging within a dry thickness range from 25 to 30 mils (0.635 to 7.62 mm)

by a single application, and the composition can be characterized as a low VOC (Volatile Organic Content) composition.

Detailed Description of the Invention

[0012] The resins of component a) are functionalized by hydroxy and/or carboxy and/or amino groups. The OH-value and the COOH-value can be, for example, in the range from 10 to 300. Particularly preferred, are hydroxy and/or carboxy functionalized resins having an OH-value in the range of 10 to 300 and a carboxy value of 10 to 50. If amino groups are present, hindered secondary amino groups are preferred.

[0013] The functionalized resins can be manufactured by polymerization reactions known by a skilled person, especially by a radical polymerization but also, e.g., by a polymerization reaction caused by a photochemical reaction or by electromagnetic radiation. Group Transfer Polymerization can also be used.

[0014] The resins can be linear, branched or star structured.

[0015] The resins, component a), are contained in the range from about 10 to 60 wt. %, preferably from about 10 wt. % to 30 wt. %, based on the coating composition.

[0016] Suitable monomers or co-monomers for the manufacture of the acrylic and methacrylic polymers of component a) may be, e.g., acrylates, methacrylates, methyl methacrylates, styrene, acrylonitrile, vinyl acetate, butadiene, including monomers, such as, acrylic acid, methacrylic acid, itaconic acid, maleic acid, crotonic acid and/or amides. To obtain the functionalized polymethacrylics and polyacrylics, suitable monomers can be incorporated into the polymer, e.g., carboxy-functionalized monomers, such as, maleic acid, acrylic acid and methacrylic acid, and, for example, hydroxy-functionalized monomers, such as, hydroxy acrylates, hydroxy methyl acrylates, propylene glycol methacrylates, butanediol monoacrylates and the like.

[0017] Suitable monomers or co-monomers for the manufacture of the functionalized polyesters may be, for example, neopentyl glycol, cyclohexanedimethanol, 1,6 hexanediol, trimethylolpropane, pentaerythritol, phthalic anhydride, isophthalic acid, hexahydrophthalic anhydride, adipic acid, azelaic acid and dimer fatty acids.

[0018] The polyesters can be, for example, linear, branched, star structured, chemically modified by urethanes, silicones, styrene, acrylics, epoxide, and the range of the OH value can be 10 to 300.

[0019] Star resins may be used as component a) and are oligomers with a star structure, which have 3 to 6 arms. Oligomers are prepared by reaction of trimethylolpropane, pentaerythritol or other multifunctional compounds with, e.g., compounds containing glycidyl groups. They include polyester bonds and both primary and secondary hydroxyl groups.

[0020] As component a) one or more acrylic, methacrylic, polyester and/or star polymers are preferred.

[0021] The crosslinking agents, component b), of the coating composition are present in the range from about 5 to 40 wt. %, preferably from about 5 wt. % to 20 wt. %, based on the coating composition.

[0022] Examples of polyisocyanates that may be used as component b) are in the free or blocked form as crosslinking agents and may include triisocyanates, diisocyanates, and cycloaliphatic diisocyanates, such as, 1,6-hexane diisocyanate, trimethylhexane diisocyanates, 1,12-dodecanediisocyanates, cyclohexane diisocyanates, isophorones, diisocyanates with cyclohexylmethane diisocyanates or mixtures thereof, and polyisocyanates derived from such diisocyanates, for example, those containing hetero atoms in the radical linking the isocyanates groups. Examples thereof include polyisocyanates containing carbo diimide groups, isocyanurate groups, urethdiol groups, urethane groups and/or biuret groups.

[0023] Suitable blocking agents for the polyisocyanate crosslinking agents described above may include the conventional, for example, CH-acidic, NH-, SH- or OH- functional blocking agents. Examples include acetyl, acetone, acetoacetic acid acyl esters, valonic acid diacyl esters, aliphatic or cycloaliphatic alcohols, oximes, lactams, imidacoles, pyracoles.

[0024] Isocyanurates, biurets, uretdions, or allofanates of 1,6-hexane diisocyanate are the preferred compounds of component b).

[0025] Examples of other crosslinkers that can be used as component b) are crosslinkers containing reactive groups, such as hydroxyl, carboxyl, amide or amino groups; cycloaliphatic, aliphatic or aromatic polyisocyanates, crosslinkers containing epoxy groups, carboxy-functional polymers that may be used as component (b) are, for example, dicyandiamide and derivatives thereof; carboxylic acids or anhydrides thereof, triglycidyl isocyanurates, polyglycidyl ethers based on diethylene glycol, glycidyl-functionalized (meth)acrylic copolymers, and dicarboxylic acids having 10 to 12 carbon atoms.

[0026] The coating composition according to the invention contains a filler material as component c). The content of this filler material component is from 5 wt. % to 70 wt. %, preferably 10 wt. % to 60 wt.%, based on the coating composition. Examples of such filler materials are aluminum hydroxide, also known as alumina trihydrate, $\text{Al}_2\text{O}_3 \cdot 3 \text{H}_2\text{O}$, calcium carbonate (CaCO_3), silica (SiO_2), magnesium hydroxide ($\text{Mg}(\text{OH})_2$), barium sulfate (BaSO_4), clays, talcs, alumina monohydrate ($\text{Al}_2\text{O}_3 \cdot \text{H}_2\text{O}$) or polymeric fillers. Preferably, aluminum hydroxide ($\text{Al}_2\text{O}_3 \cdot 3 \text{H}_2\text{O}$) is used as component c).

[0027] The component d) is a small-grained solid material, which is different from component c), and is a ground polymer material. The content of this component d) is from 0 wt. % to 40 wt. %, preferably 2 wt. % to 30 wt.%, based on the coating composition.

[0028] This material can be based on polymethyl methacrylate (pMMA), crosslinked unsaturated polyester, epoxide or other polymeric material - filled or unfilled.

[0029] This material can be ground or calendered by mills, grinders or calender to small particles like granules, crunchies, flakes, and powder particles. The material can be toned in different colors or in one color. Examples of additives used in this material are, e.g., colorants, antioxidants, catalysts, light stabilizers, and also fillers. One example for the component d) is a filled polymer material consisting of about 40 % of polymethyl methacrylate, of about 60 % of aluminum hydroxide, colorants, and other additives at low levels, for example, known under the name of Corian®, which is a product of DuPont.

[0030] Examples of organic solvents that may be used in the coating composition according to the invention as component e) include glycol ethers, such as, butyl glycol, butyl diglycol, dipropylene glycol, dimethyl ether, dipropylene glycol monomethyl ether, ethylene glycol dimethyl ether; glycol ether esters, such as, ethyl glycol acetates, butyl diglycol acetates, methoxypropyl acetates; esters, such as, ethyl acetate, butyl acetate, isobutyl acetate, amyl acetate; ketones, such as, methyl ethyl ketone, methyl propyl ketone, methyl isopropyl ketone, methyl isobutyl ketone, diisobutyl ketone, methyl amyl ketone, cyclohexanone, isophorones; alcohols, such as, methanol, ethanol, propanol, butanol; aromatic hydrocarbons, such as, toluene, xylenes, Solvesso® 100 (mixture of aromatic hydrocarbons with a boiling range from 155 to 185 °C), Solvesso® 150 (mixture of aromatic hydrocarbons with a boiling range from 182 to 202 °C), and aliphatic hydrocarbons.

[0031] The organic solvents are contained in the range from 0 to 35 wt. %, preferably in a range of 10 to 25 wt. %, based on the coating composition, in the case of liquid compositions according to the invention.

[0032] Solid compositions according to the invention do not contain any organic solvent as component e).

[0033] The coating composition may contain conventional coating additives in total amount up to 15 wt. % based on coating composition ready for application, for example, leveling and anticratering agents, defoamers, dispersing and wetting additives, rheological modifiers, such as, pyrogenic silica, modified clays, polyamides and urea group-containing reaction products of amines (sagging control agents), catalysts, colorants, light stabilizers, UV absorbers, antioxidants and the like.

[0034] Depending on the intended use of the coating composition and on the integrated components, the coating composition may be unpigmented (transparent), translucent, or contain pigments. They may therefore contain fillers, which are different from the component c) and/or transparent, color imparting and/or special effect-imparting pigments. Examples of inorganic or organic color-imparting pigments include titanium dioxides, micronized titanium dioxide, iron oxide pigments, carbon black, azo pigments, phthalocyanine pigments, quinacridone or pyrrololpyrrole pigments. Examples of special effect-imparting pigments include metallic pigments, interference pigments, e.g., metal oxide coated metallic pigments, e.g., titanium dioxide-coated or mixed oxide-coated aluminum, coated mica, e.g. titanium dioxide-coated mica and graphite effect like special-effect pigments. Examples of suitable fillers include aluminum trihydrate, silica, aluminum silicates, barium sulfates, calcium carbonates, and talc.

[0035] Optionally, any material may be added for a decorative effect. Decorative additives, such as, crushed stones, gemstones, metal flake or fillings, micas, seashells, pearls, colored or transparent polymeric particles or fibers, mirrored particles and pigments may be added in quantities according to taste or fashion. However, these quantities usually do not exceed 5% by weight, preferably 2% by weight. The decorative additives may be thoroughly mixed with the other components or placed on the surface.

[0036] Liquid coating composition according to this invention may contain reactive thinners as component (g) in the range of 0 to 30 wt.%, preferred in the range of 2 to 10 wt.%.

[0037] Examples for the thinners are ketimines, aminofunctional compounds, such as, for example, 1-aza-3,7-dioxo-bicyclo-2,8-diisopropyl-5-ethyl(3.3.0)octane and also oxazolidine derivatives, such as, for example, 3-ethyl-2-methyl-2-(3-methylbutyl)-1,3-oxazolidine.

[0038] The use of oxazolidines is preferred.

[0039] Solid compositions according to this invention do not contain any reactive thinners as component g).

[0040] The coating composition according to the invention may have a uniform color, a stone-like and/or a special aesthetic.

[0041] The liquid coating composition according to the invention in the state ready for application has a solids content, formed from the resins solids and the optionally contained non-volatile additives and optionally contained pigments, from 40 wt. % to 80 wt. %. The coating composition contains, as volatile constituents, organic solvents as mentioned above.

[0042] The coating composition can take the form of a one-component coating composition or a two-component composition. In case of a two-component coating composition, one component contains the resins of component a) and the other component contains the polyisocyanates. The other components of the coating composition according

to the invention, that means the aluminum hydroxide, the ground material, organic solvents, additives and thinners may be presented in either one or in both of the two components. Preferably they may be present in the component which contains the resins of component a).

[0043] The coating composition according to the invention may be used in the preparation of a one-layer coating on any substrates of, for example, metal, plastic, or substrates composed of a mixed construction of metal and plastic and of any other material, for example, clay, tile, woven glass fiber, masonites and the like. Substrates employed include also plywood, particle board, medium-density fiber board (MDF board), tile board. These substrates can be used as products, such as, existing and in place counter tops, cabinets, wall panels, furniture, slab boards, ceramic tile, high pressure laminate (HPL), low pressure laminate and other such laminates, stainless steel, gypsum board, glass and the like. The coating composition may also be applied directly over ceramic tile/group installations in such a way that a seamless surface is formed with tile-like appearance.

[0044] The coating composition according to the invention can be applied directly on the untreated surface of a substrate, for example, of a porous substrate. It is also possible to use the coating composition according to the invention for a multi-layer coating of the substrate whereby the multi-layer coating may consist of several coating layers of the coating composition of the invention. Smooth or glass like surface should be coated, for example, by an 2-pack epoxy primer or other appropriate primer to ensure proper adhesion of the coating composition according to the invention. Preferably the coating composition is used as a direct coating of the untreated surface of a porous substrate.

[0045] In the event the coating composition is used for outdoor purposes, for example, on the exterior of a building, the weatherability of the composition can be improved by the addition of an ultraviolet light stabilizer or a combination of ultraviolet light stabilizers in the amount of 0.1% to 5% by weight, based on the weight of the composition. Such stabilizers include ultraviolet light absorbers, screeners, quenchers, and specified hindered amine light stabilizers. Also, an antioxidant can be added, in the amount 0.1% to 2% by weight, based on the weight of the composition.

[0046] Typical ultraviolet light stabilizers that are useful include benzophenones, triazoles, triazines, benzoates, hindered amines and mixtures thereof. Specific examples of ultraviolet stabilizers are disclosed in U.S. Patent 4,591,533. Typically useful hindered amine light stabilizers that can be used are, for example, Tinuvin® 928 and Tinuvin® 123 or mixtures thereof, commercially available from Ciba Specialty Chemicals, Tarrytown, New York.

[0047] The coating composition according to the invention can be applied by known methods. In the case of liquid compositions, they can be applied, e.g., via commercial spray gun equipment, preferably by spray gun with a pressured upper container. Solid compositions can be applied by known electrostatic spraying processes used for the application of powder coating compositions, for example, corona or tribo spray guns can be used and other suitable powder application processes, for example, an aqueous dispersion of the solid powder composition (aqueous powder slurry) can be applied or a broad band spreading process can be used to apply the composition.

[0048] Particularly, the composition according to the invention in the dry or liquid form can be applied in a dry layer thickness of, for example, 25 to 30 mils (0.635 to 0.762 mm) regarding a one-layer application and in a dry film thickness of, for example, 45 to 50 mils (1.143 to 1.27 mm) by a multi-layer deposition of the coating composition. The final coating thickness can be designed to be, for example, 60 to 80 mils (1.524 to 2.032 mm) or thicker and can be built in 25 to 30 mils (0.635 to 0.762 mm) increments per single application depending on the intended use.

[0049] The applied coating composition according to the invention can be cured by crosslinking at ambient temperature as well as at elevated temperature. It is desirable, but not necessarily, to have a short flash-off phase before start of the curing step at elevated temperature. The curing temperature can vary from 15 to 100 °C, particularly from 25 to 80 °C. The curing times are, for example, of the order of magnitude of 20 min. to 24 hours. Preferably the coating composition according to the invention is crosslinked at ambient temperature in the range of 15 to 35 °C, preferably of 20 to 30 °C in the time range to 24 hours. If forced drying is applied for curing, temperature range 60 to 100 °C is recommended, preferably of 60 to 80 °C, in a time range of 20 to 60 minutes. A hard, crosslinked surface is obtained with a glossy lacquer-like appearance having good resistance to chemicals, outstanding mar resistance and very good optical properties.

[0050] The cured coating can be sanded and/or polished to achieve a smooth surface of a desired thickness. The coated substrate or article can be cut into desired shapes.

[0051] The cured surface has a high quality that means scratch-resistance, stain-resistance, heat-resistance, chip-resistance and superior hardness. The sanding can be used to reduce the thickness to a desired value, to obtain a smooth surface and/or to bring out an aesthetic quality.

[0052] It is possible to replace solid and/or cast materials, such as, marble or granite slabs, walls, panels and the like by substrates coated with the coating composition according to the invention with a high stability and strength as well as a high weatherproof property with a good heat and stain resistance.

[0053] The coating composition can also be used for store fixtures, vertical surfacing on substrates of all types and also horizontal surfacing. It could replace wallpaper. Formulations can be used outdoors as architectural facings, for example, with a proper UV stabilization.

[0054] The following examples illustrate the invention. All parts and percentages are on a weight basis unless oth-

erwise noted. Molecular weights are determined by gel permeation chromatography using polymethylmethacrylate as the standard.

Examples

Example 1

Preparation of coating compositions of the invention

[0055]

Composition 1:		
	Part A	Wt. %
1	Desmophen® A 265 BA (Acrylic polymer with 2 % of OH groups, 65 wt.% in butyl acetate, manufactured by Bayer)	10.35
2	Desmophen® 670 BA (Polyester resin with 6,7 % of OH groups, 80 wt.% in butyl acetate, manufactured by Bayer)	7.75
3	Methyl isobutyl ketone, solvent	14.92
4	Pot-life retarder (2,4-pentane dione)	1.21
5	Catalyst (1,4-diazabicyclo[2.2.2]octane, 33 wt.% in dipropylene glycol)	0.077
6	Catalyst (100 % dibutyltin dilaurate)	0.003
7	EFKA®-2022 (Organically modified polysiloxane in solvent mixture, defoamer, manufactured by EFKA® Additives, the Netherlands)	1.10
8	EFKA®-3031 (52 wt. % organically modified polysiloxane in alkyl benzene, leveling and anticratering agent, manufactured by EFKA® Additives, the Netherlands)	0.29
9	EFKA®-4047 (35% wt. % high molecular weight modified polyurethane in butyl acetate, dispersing additive, manufactured by EFKA® Additives, the Netherlands)	1.03
10	Thixatrol® Plus (polyamide, rheological additive, manufactured by Elementis)	0.28
11	Aerosil® R972 (Fumed silica hydrophobically modified rheological additive having a BET value of 110 m ² /g, manufactured by Degussa)	1.45
12	Aluminum trihydrate, filler	12.91
13	Hindered Amine Light Stabilizer [Bis(1,2,2,6,6-pentamethyl-4-piperidyl) sebacate and methyl (1,2,2,6,6-pentamethyl-4-piperidyl) sebacate]	0.23
14	UV absorber (Methyl-3-[3-(2H-benzotriazol-2-yl)-5-tert.butyl-4-hydroxyphenyl]propionate)	0.46
15	Corian® Crunchies (Ground polymer material of polymethylmethacrylate filled with alumina trihydrate and various fillers)	28.36
Part B		
	Activator (Hexamethylene diisocyanate isocyanurate, 19.6 % NCO, 90 wt. % in butyl acetate)	10.14
Thinner		
	Ethyl acetate	9.44

[0056] Components 1 to 14 are premixed by high-speed disperser and then ground in bead mill to fineness of grinding 6 of Hegman scale. The resulting composition is immediately mixed with component 15 - ground polymer material.

[0057] Before application, Part A is mixed with Part B in weight ratio 100 : 12.6 and thinned by approx. 9 wt.% of Thinner to application viscosity - flow time 25 seconds using a Ford Cup with jet diameter 6 mm. Evaluation of the flow time is performed according to ASTM D-1200 at 25 °C.

Composition 2:

Part A		
1	Potlife retarder (2,4-pentane dione)	Wt. %
2	Aerosil® R972 (described above)	2.01
3	Aluminum trihydrate, filler	0.67
4	Corian® Crunchies (described above)	27.79
5	Catalyst (1,4-diazabicyclo[2.2.2]octane, 33 wt.% in dipropylene glycol)	11.66
6	Catalyst (100 % dibutyltin dilaurate)	0.155
7	Desmophen® A 365 BA/X (acrylic polymer with 2.9% of OH groups, 65 wt. % in butyl acetate/xylene, manufactured by Bayer)	0.005
8	Dukon 21 (80 wt. % star polymer with 4.9 % of OH groups in butyl acetate, manufactured by Spolek, the Czech Republic)	18.62
9	EFKA®-2023 (Organically modified polysiloxane in solvent mixture, defoamer, manufactured by EFKA® Additives, the Netherlands)	4.95
10	EFKA®-3772 (60 wt. % fluorocarbon modified polyacrylate in secondary butanol, leveling and anticratering agent, manufactured by EFKA® Additives, the Netherlands)	0.30
11	EFKA®-8530 (100 % aliphatic polyether with acidic groups, dispersing additive, manufactured by EFKA® Additives, the Netherlands)	0.99
12	Ethyl acetate, solvent	1.03
13	Thixatrol® Plus (described above)	8.92
14	Hindered Amine Light Stabilizer (described above)	0.26
15	UV absorber (described above)	0.23
	Part B	0.46
	Activator (described above)	
	Thinner	9.51
	Aromatic hydrocarbon	
	Ethyl acetate	5.72
		5.72

[0058] Components 1 to 15 (except component 4) are premixed by high-speed disperser and then ground in bead mill to fineness of grinding 6 of Hegman scale. The resulting composition is immediately mixed with component 4.

[0059] Before application, Part A is mixed with Part B in weight ratio 100 : 12 and thinned by approximately 13 wt. % of Thinner to application viscosity-flow time 22 seconds using a Ford Cup with jet diameter 6 mm. Evaluation of the flow time is performed according to ASTM D-1200 at 25 °C.

Composition 3:

Part A		
		Wt. %
	Duroftal® VPI 2801 (Polyester with 6.6 % OH, 80 wt. % in butyl acetate, manufactured by Solutia)	16.65
	Desmophen® VP LS 2973 (Aminofunctional polyester reactive thinner, ekv. weight 396, manufactured by Bayer)	3.72
	Butyl acetate, solvent	
	Catalyst (1,4-diazabicyclo[2.2.2]octane, 33 wt. % in dipropylene glycol)	4.73
	Catalyst (100 % dibutyltin dilaurate)	0.024
	EFKA®-2022 (Defoamer - described above)	0.006
		1.10

(continued)

Composition 3:	
Part A	Wt. %
EFKA®-3772 (Fluorocarbon modified polyacrylate - described above)	0.99
EFKA®-4047 (Dispersing additive - described above)	1.03
Hindered Amine Light Stabilizer (Described above)	0.53
UV absorber (Described above)	1.10
Thixatrok® ST (100 % castor oil derivative rheological additive)	0.50
Aerosil® R972 (Fumed silica - described above)	0.27
Aluminum trihydrate, filler	21.56
Barium sulfate	6.90
Part B	
Hexamethylene diisocyanate uretdione activator (100 %, 21.8 % NCO)	12.63
Butyl acetate, solvent	5.22
Corian® Crunchies (described above)	18.20
Thinner	
Ethyl acetate	4.84

[0060] All components of Part A are premixed by high-speed disperser and then ground in bead mill to fineness of grinding 6 of Hegman scale.

[0061] Part B preparation: Corian® Crunchies are added in small amounts to the solution of Activator in butyl acetate and the mixture is homogenized by high-speed dissolver.

[0062] Before application, Part A is mixed with Part B in weight ratio 100 : 61 and thinned by approx. 5 wt. % of Thinner to application viscosity - flow time 22 seconds using a Ford Cup with jet diameter 6 mm. Evaluation of the flow time is performed according to ASTM D-1200 at 25 °C.

Example 2

Application on plywood substrate:

[0063] A mixture of both part A and B of Composition 2 from Example 1 is applied by spray gun with pressured upper container and jet nozzle diameter 2.3 mm on a plywood substrate. The pressure on spray gun jet nozzle is about 0.2 MPa and the overpressure in upper container is about 7 kPa. Wet thickness of the first layer should be maximally 10 mils (0.250 mm) to ensure good adhesion and low content of entrapped solvents close to the surface. After 1 hour of drying at ambient temperature the film is force-dried in oven for one hour at 60 °C. The second and the next layers are sprayed on the force-dried film after the substrate is cooled to room temperature and the thickness is about 20 to 30 mils (0.508 to 0.762 mm). The resulting film is force dried at 60 °C for 1 hour or can be dried at room temperature for at least 24 hours before the next layer is applied. When the required thickness is reached, 60 to 80 mils (1.524 to 2.032 mm), the films are post-cured at 60 to 80 °C for several hours to accelerate the hardness development and to improve sandability.

Example 3

Application on glazy ceramic tiles:

[0064] Commercially available two-pack epoxy primer was mixed with hardener and thinned to an application viscosity (flow time 18 to 20 seconds at Ford Cup with jet diameter 4 mm). A layer of film is applied by spraying on the tile substrate with a spray gun having a jet nozzle diameter of 18 mm and a jet nozzle pressure 0.17 to 0.2 MPa.

[0065] The primer was applied on smooth glazy ceramic tiles in wet thickness about 0.100 mm. This film was allowed to dry at ambient temperature for 24 hours.

[0066] The mixture of both part A and B of Composition 1 from Example 1 was applied by spray gun with pressured upper container and jet nozzle diameter 2.3 mm. The pressure on spray gun jet nozzle is about 0.2 MPa and the overpressure in upper container is about 7 kPa. Each applied layer has a dry film thickness about 20 to 30 mils (0.508 to 0.762 mm).

[0067] The first layer is dried for 1 hour at ambient temperature and then the film is force-dried in oven for one hour at 60 °C. The second and the next layers are sprayed on the force-dried film after the substrate is cooled to room temperature. Forced drying at 60 °C for 1 hour or room temperature drying for at least 24 hours is necessary before the next layer is applied. When the required thickness is reached, 60 to 80 mils (1.524 to 2.032 mm), the coated films are cured at ambient temperature for several days to achieve appropriate film hardness for good sandability.

Example 4

Application on particle board substrate:

[0068] A mixture of both part A and B of Composition 3 from Example 1 is applied by spray gun with pressured upper container and jet nozzle diameter 2.3 mm on a substrate. The pressure on spray gun jet nozzle is about 0.2 MPa; the overpressure in upper container is about 7 kPa.

[0069] Wet thickness of the first layer should be maximally 10 mils (0.250 mm) to ensure good adhesion and low content of entrapped solvents close to the surface. After 1 hour of drying at ambient temperature the film is force-dried in oven for one hour at 60 °C. The second and the next layers are sprayed on the force-dried film after the substrate is cooled to room temperature and can be thicker- about 20 to 30 mils (0.508 to 0.762 mm). The film layers are forced dried at 60 °C for 1 hour or can be dried at room temperature drying for at least 24 hours before the next layer is applied. When the required thickness is reached 60 to 80 mils (1.524 to 2.032 mm), the coated films are post-cured at 60 to 80 °C for several hours to accelerate the hardness development and to improve sandability.

Claims

1. A coating composition comprising

- (a) 10 to 60 wt. % of a functionalized solid resin having functional groups selected from the group consisting of hydroxy-, carboxy-, amino- and any mixtures thereof and wherein the functionalized solid resins are selected from the group consisting of methacrylic resins, acrylic resins, polyester resins, polyurethane resins, epoxy modified resins with linear, branched or star structure,
- (b) 5 to 40 wt. % of at least one crosslinking agent for component (a),
- (c) 5 to 70 wt. % of filler material,
- (d) 0 to 40 wt. % of a ground polymer material,
- (e) 0 to 35 wt. % of organic solvents,
- (f) 0.01 to 15 wt. % of additives and pigments and
- (g) 0 to 30 wt. % reactive thinners.

2. The coating composition according to claim 1 wherein the composition is a flowable liquid composition and wherein the crosslinking agent for component

- (a) comprises a polyisocyanate selected from the group consisting of blocked polyisocyanates and unblocked polyisocyanates.

3. The coating composition according to claim 1 comprising

- (a) 10 to 60 wt. % of a functionalized solid resin having functional groups selected from the group consisting of hydroxy-, carboxy-, amino- and any mixtures thereof and wherein the functionalized solid resins are selected from the group consisting of methacrylic resins, acrylic resins, polyester resins, polyurethane resins, epoxy modified resins with linear, branched or star structure,
- (b) 5 to 40 wt. % of at least one crosslinking agent selected from the group consisting of hydroxyl, carboxyl, amide or amino group containing crosslinkers, cycloaliphatic aliphatic or aromatic polyisocyanates, epoxy group containing crosslinkers, and carboxy-functional polymers;
- (c) 5 to 70 wt. % of filler material,
- (d) 0 to 40 wt. % of a ground polymer material,

(f) 0.01 to 15 wt. % of additives and pigments.

4. The composition according to claims 1 to 3 wherein one or more resins selected from the group consisting of acrylic resins, methacrylic resins, polyester resins and resins with star structure are used as component (a).
5. The composition according to claims 1 to 3 wherein component (b) is selected from the group consisting of isocyanurates, biurets, uretdions and allofanates of 1,6-hexane diisocyanate.
6. The composition according to claims 1 to 5 wherein component (c) is aluminum hydroxide.
7. The composition according to claims 1 to 6 wherein component (c) comprises 10 to 60 wt. % of the coating composition.
8. The composition according to claims 1 to 7 wherein component d) comprises 2-30 wt.% polymethyl methacrylate containing filler.
9. The composition according to claim 8 wherein component d) consists of about 40 wt. % polymethyl methacrylate, and 60 wt. % of aluminum hydroxide, colorants, and other additives at low levels.
10. The composition according to claim 1,2, 4 to 8 wherein the amount of the organic solvents is from 10 to 35 wt. %.
11. A process for coating a substrate which comprises applying a one-coat layer on a substrate using a coating composition according to claims 1 to 3 and curing said coating.
12. A process for forming a multi-layer coating which comprises applying several coating layers to a substrate being applied from the coating composition according to claims 1 to 3 and curing said coating layers.
13. A process for forming a coating layer as one-coating layer of a multi-layer coating which comprises applying to a substrate a coating layer selected from the group consisting of externally pigmented top coat layer and transparent clear coat layer said coating layer being applied from the coating composition according to claims 1 to 3 and curing said coating layer.
14. A substrate coated with the coating composition according to claims 1 to 3 and then cured.

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 362 874 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
02.01.2004 Bulletin 2004/01

(51) Int Cl.7: **C08G 18/62**, C09D 175/04,
B05D 1/00, C08G 18/42,
C09D 175/06, C08K 3/00,
C08G 18/58

(43) Date of publication A2:
19.11.2003 Bulletin 2003/47

(21) Application number: **03076734.7**

(22) Date of filing: **12.05.2003**

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PT RO SE SI SK TR**
Designated Extension States:
AL LT LV MK

(72) Inventors:
• Milic, Richard
Hradec Kralove, CZ-500 03 (CZ)
• Kupcakova, Zdenka
Pardubice, CZ-530 09 (CZ)

(30) Priority: **15.05.2002 US 146162**

(71) Applicant: **E.I. DU PONT DE NEMOURS AND
COMPANY**
Wilmington Delaware 19898 (US)

(74) Representative:
**DuPont Performance Coatings Christine
Biering/Christine Kimpel
Dupont Performance Coatings GmbH & Co.KG,
Patent and License Departement,
Christbusch 25
42285 Wuppertal (DE)**

(54) **A decorative coating composition for solid substrates**

(57) A coating composition comprising

(f) 0.01 to 15 wt. % of additives and pigments and
(g) 0 to 30 wt. % reactive thinners.

- (a) 10 to 60 wt. % of one or more hydroxy-, carboxy-
and/or amino-functionalized solid resins selected
from the group of methacrylic resins, acrylic resins,
polyester resins, polyurethane resins, epoxy modi-
fied resins with linear, branched or star structure,
(b) 5 to 40 wt. % of one or more crosslinking agents
for component (a),
(c) 5 to 70 wt. % of a filler, such as, aluminum hy-
droxide,
(d) 0 to 40 wt. % of a ground polymer material,
(e) 0 to 35 wt. % of organic solvents,

EP 1 362 874 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 03 07 6734

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	US 6 271 293 B1 (NAKAI HIROSHI ET AL) 7 August 2001 (2001-08-07) * column 1, line 4 - line 15 * * example 15 *	1-14	C08G18/62 C09D175/04 B05D1/00 C08G18/42 C09D175/06
X	EP 0 872 338 A (DAINIPPON PRINTING CO LTD) 21 October 1998 (1998-10-21) * page 2, line 5 - line 7 * * example 4 *	1-14	C08K3/00 C08G18/58
X	US 4 578 418 A (KRUEGER ACHIM R) 25 March 1986 (1986-03-25) * example 1D *	1-14	
X	DE 43 38 265 C (HERBERTS GMBH) 8 December 1994 (1994-12-08) * example 1 * * claim 1 *	1-14	
X	US 4 609 690 A (GRUBER NORMA J ET AL) 2 September 1986 (1986-09-02) adhesive no. 121D * column 3, line 3 - line 6 *	1-14	TECHNICAL FIELDS SEARCHED (Int.Cl.7)
X	DE 44 33 854 A (BASF LACKE & FARBEN) 28 March 1996 (1996-03-28) * claims 1,3 *	1-14	C08G C09D B05D C08K
X	US 4 102 847 A (HARTMANN HEINRICH ET AL) 25 July 1978 (1978-07-25) * claims 1,4; example 1 *	1-14	
X	US 5 278 223 A (GRUENWAEELDER BERNHARD ET AL) 11 January 1994 (1994-01-11) * example 1 * * column 4, line 60 - line 61 *	1-14	
		-/--	
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 22 October 2003	Examiner Müller, M
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 02 (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 03 07 6734

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	US 5 804 646 A (BAYARDS RICHARD A ET AL) 8 September 1998 (1998-09-08) * example VIII *	1-14	
X	US 5 472 649 A (CHANG YEONG-HO ET AL) 5 December 1995 (1995-12-05) * example 4 *	1-14	
X	US 5 468 461 A (HOSODA YASUSHI ET AL) 21 November 1995 (1995-11-21) * example 27 *	1-14	
X	US 4 877 656 A (BASKIN DAVID) 31 October 1989 (1989-10-31) * column 1, line 8 - line 10 * * column 4, line 63 - line 68 *	1-14	
X	US 3 341 396 A (IVERSON ELIZABETH M) 12 September 1967 (1967-09-12) * column 1, line 30 - line 31 * * example III *	1-14	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
<p>The present search report has been drawn up for all claims</p>			
Place of search MUNICH		Date of completion of the search 22 October 2003	Examiner Müller, M
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.82 (P04C01)



European Patent
Office

Application Number

EP 03 07 6734

CLAIMS INCURRING FEES

The present European patent application comprised at the time of filing more than ten claims.

- ☐ Only part of the claims have been paid within the prescribed time limit. The present European search report has been drawn up for the first ten claims and for those claims for which claims fees have been paid, namely claim(s):
- ☐ No claims fees have been paid within the prescribed time limit. The present European search report has been drawn up for the first ten claims.

LACK OF UNITY OF INVENTION

The Search Division considers that the present European patent application does not comply with the requirements of unity of invention and relates to several inventions or groups of inventions, namely:

see sheet B

- ☐ All further search fees have been paid within the fixed time limit. The present European search report has been drawn up for all claims.
- ☐ As all searchable claims could be searched without effort justifying an additional fee, the Search Division did not invite payment of any additional fee.
- ☒ Only part of the further search fees have been paid within the fixed time limit. The present European search report has been drawn up for those parts of the European patent application which relate to the inventions in respect of which search fees have been paid, namely claims:
1-14 (first, second and fourth alternative)
- ☐ None of the further search fees have been paid within the fixed time limit. The present European search report has been drawn up for those parts of the European patent application which relate to the invention first mentioned in the claims, namely claims:



European Patent
Office

LACK OF UNITY OF INVENTION
SHEET B

Application Number
EP 03 07 6734

The Search Division considers that the present European patent application does not comply with the requirements of unity of invention and relates to several inventions or groups of inventions, namely:

1. Claims: 1-14 (first alternative)

Coating composition comprising certain amounts of
(a) a functionalized methacrylic or acrylic resin,
(b) a crosslinking agent for component (a),
(c) a filler material and
(d) additives and pigments.

2. Claims: 1-14 (second alternative)

Coating composition comprising certain amounts of
(a) a functionalized polyester resin,
(b) a crosslinking agent for component (a),
(c) a filler material and
(d) additives and pigments.

3. Claims: 1-14 (third alternative)

Coating composition comprising certain amounts of
(a) a functionalized polyurethane resin,
(b) a crosslinking agent for component (a),
(c) a filler material and
(d) additives and pigments.

4. Claims: 1-14 (fourth alternative)

Coating composition comprising certain amounts of
(a) a functionalized epoxy modified resin,
(b) a crosslinking agent for component (a),
(c) a filler material and
(d) additives and pigments.

ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 03 07 6734

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

22-10-2003

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 6271293	B1	07-08-2001	JP 3009361 B2	14-02-2000
			JP 10152646 A	09-06-1998
			JP 3009363 B2	14-02-2000
			JP 10102000 A	21-04-1998
			JP 3161590 B2	25-04-2001
			JP 10168386 A	23-06-1998
			JP 3161591 B2	25-04-2001
			JP 10168382 A	23-06-1998
			JP 3161593 B2	25-04-2001
			JP 10259354 A	29-09-1998
			CN 1427054 A	02-07-2003
			CN 1246884 A ,B	08-03-2000
			WO 9822547 A1	28-05-1998
			US 2002077397 A1	20-06-2002
EP 0872338	A	21-10-1998	JP 10067085 A	10-03-1998
			AU 730837 B2	15-03-2001
			AU 4031497 A	19-03-1998
			BR 9706666 A	20-07-1999
			EP 0872338 A1	21-10-1998
			NZ 330255 A	30-08-1999
			US 6103352 A	15-08-2000
			CA 2235542 A1	05-03-1998
			CN 1206374 A ,B	27-01-1999
			WO 9808682 A1	05-03-1998
			TW 460387 B	21-10-2001
US 4578418	A	25-03-1986	AU 1036988 A	28-04-1988
			AU 8973982 A	05-05-1983
			BR 8206138 A	20-09-1983
			CA 1185727 A1	16-04-1985
			DE 3271265 D1	26-06-1986
			DK 469582 A	27-04-1983
			EP 0078172 A2	04-05-1983
			GB 2108138 A ,B	11-05-1983
			JP 1660866 C	19-05-1992
			JP 3026229 B	10-04-1991
			JP 58080339 A	14-05-1983
			MX 160860 A	05-06-1990
			MY 11786 A	31-12-1986
			NO 823531 A	27-04-1983
			US 4522879 A	11-06-1985
			ZA 8207782 A	27-06-1984
DE 4338265	C	08-12-1994	DE 4338265 C1	08-12-1994

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 03 07 6734

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

22-10-2003

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4609690 A	02-09-1986	US 4491646 A	01-01-1985
		AU 548554 B2	19-12-1985
		AU 3366984 A	04-04-1985
		CA 1267992 A1	17-04-1990
		DE 3435777 A1	11-04-1985
		DK 463784 A ,B,	30-03-1985
		FI 843811 A ,B,	30-03-1985
		JP 60092376 A	23-05-1985
		NO 843873 A ,B,	01-04-1985
		SE 463923 B	11-02-1991
		SE 8404842 A	30-03-1985
DE 4433854 A	28-03-1996	DE 4433854 A1	28-03-1996
		BR 9504117 A	06-08-1996
US 4102847 A	25-07-1978	DE 2539104 A1	10-03-1977
		FR 2322911 A1	01-04-1977
		GB 1550409 A	15-08-1979
		IT 1064916 B	25-02-1985
		SE 416057 B	24-11-1980
		SE 7609667 A	04-03-1977
US 5278223 A	11-01-1994	DE 3932171 A1	04-04-1991
		AT 109489 T	15-08-1994
		CA 2066649 A1	28-03-1991
		DD 298130 A5	06-02-1992
		DE 59006724 D1	08-09-1994
		WO 9104998 A1	18-04-1991
		EP 0494219 A1	15-07-1992
		ES 2057590 T3	16-10-1994
		FI 921265 A	24-03-1992
		NO 921029 A	17-03-1992
		PL 287052 A1	13-01-1992
		SK 470590 A3	05-08-1998
		ZA 9007703 A	29-05-1991
US 5804646 A	08-09-1998	BE 1008721 A3	02-07-1996
		CN 1120058 A ,B	10-04-1996
		DE 69515406 D1	13-04-2000
		DE 69515406 T2	02-11-2000
		EP 0703256 A1	27-03-1996
US 5472649 A	05-12-1995	WO 9528434 A1	26-10-1995
US 5468461 A	21-11-1995	JP 5331412 A	14-12-1993
		DE 69305111 D1	07-11-1996

EPO FORM P459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

ANNEX TO THE EUROPEAN SEARCH REPORT ON EUROPEAN PATENT APPLICATION NO.

EP 03 07 6734

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

22-10-2003

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5468461 A		DE 69305111 T2	22-05-1997
		EP 0573016 A1	08-12-1993
		KR 133273 B1	16-04-1998
US 4877656 A	31-10-1989	AT 123718 T	15-06-1995
		DE 68923039 D1	20-07-1995
		EP 0356148 A2	28-02-1990
		US 4956030 A	11-09-1990
US 3341396 A	12-09-1967	NONE	

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82